

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08L 53/00, 75/04, 87/00, C08K 7/14	A1	(11) International Publication Number: WO 99/13004 (43) International Publication Date: 18 March 1999 (18.03.99)
(21) International Application Number: PCT/NL98/00522 (22) International Filing Date: 9 September 1998 (09.09.98) (30) Priority Data: 1007000 11 September 1997 (11.09.97) NL (71) Applicant (for all designated States except US): DSM N.V. [NL/NL]; Het Overloon 1, NL-6411 TE Heerlen (NL). (72) Inventors; and (75) Inventors/Applicants (for US only): BORGGREVE, Reinoldus, Jozef, Maria [NL/NL]; Frank Smitsstraat 1, NL-6336 VG Hulsberg (NL). LEUNG, Tsui, Wah, Christina [NL/SG]; 564 Upper East Coast Road, Fairview Court, Singapore 466 582 (SG). (74) Agent: ALFENAAR, Marinus; Octrooibureau DSM, P.O. Box 9, NL-6160 MA Geleen (NL).		(81) Designated States: AL, AU, BA, BB, BG, BR, CA, CN, CU, CZ, EE, GE, HR, HU, ID, IL, IS, JP, KP, KR, LC, LK, LR, LT, LV, MG, MK, MN, MX, NO, NZ, PL, RO, SG, SI, SK, SL, TR, TT, UA, US, UZ, VN, YU, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: PROCESS FOR PRODUCING ARTICLES HAVING A SOFT TOUCH		
(57) Abstract The invention relates to a process for producing a product that is pleasant to touch, essentially comprising the single-step injection moulding of a thermoplastic elastomer composition, chosen from the group comprising polyester block copolymers, polyurethanes and styrene block copolymers, which contains glass fibre. Preferably a polyether ester with a Shore D hardness of between 30 and 50 and an MFI of 10-50 g/10 min. containing 35-55 wt.% glass fibre is used in the composition. The product obtained preferably has a stiffness of at least 2000 MPa and a Shore D hardness of less than 60.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

- 1 -

PROCESS FOR PRODUCING ARTICLES
HAVING A SOFT TOUCH

5

The invention relates to a process for producing products having a soft touch. Consumers are imposing increasingly higher demands on articles to be bought by them. In addition to durability and ease of use, an aesthetic appearance, for example, is demanded. Besides design, the latter demand can be translated into a perfect product surface. These aesthetic demands have now evolved to such an extent that, in addition to the eye, the tactile sense has to be pleasantly stimulated when the aforementioned product is handled. Products that must meet the aforementioned demands are for example housings of electric and electronic equipment, for example mobile telephones, remote controls of televisions and other audio and/or visual playing and recording equipment and so-called personal organizers, handles, arms of chairs, steering wheels, switches and keys. These products also demand a good stiffness and must be able to withstand rough treatment.

To obtain products that meet this set of requirements, producers according to the state of the art have to resort to complex production methods that raise costs substantially. For a recent survey of the market and technology reference is made to 'Plastics News' of 21 July 1997, 'Soft touches for soft-touch products'.

- 2 -

A known process is that according to which the product is obtained from a stiff polymer composition by means of injection-moulding and is subsequently coated with a soft polymer that is pleasant to touch.

- 5 Technical problems that have to be solved are then for example that the polymer composition employed must have both stiffness and ductility and the coating to be applied must show good adhesion to the stiff polymer composition.

- 10 This combination of requirements limits the choice of materials. For mobile telephones and the like use is usually made of a stiff polymer composition of acrylonitrile-butadiene-styrene copolymer with polycarbonate (ABS + PC) and a coating of a polyurethane
15 with long alcohol segments.

- The use of cheaper (less stiff) polymers, for example reinforced with glass fibre, involves the drawback that they usually show an imperfect surface, as a result of which a thicker coating of the relatively
20 expensive polyurethane is required to conceal these imperfections. The coating is applied with the aid of conventional means or by means of sequential moulding.

- Another (known) process is that according to which the surface of the product obtained from a stiff
25 polymer is provided with a fine texture that is pleasant to touch. An example is a texture corresponding to that of an orange peel. This texture can sometimes be applied afterwards, or has to be applied already in a negative form in the wall of the mould in which the product is
30 produced, which is a difficult and cost-raising

operation whose result is generally not considered optimum by consumers.

The inventors have now succeeded in finding a simple process according to which a product having the
5 combination of desired properties indicated above is obtained in a single operation.

The process according to the invention for producing products that are pleasant to touch comprises the single-step injection-moulding of a glassfibre-
10 reinforced thermoplastic elastomer chosen from the group comprising polyester block copolymers, polyurethane and styrene block copolymers.

The thermoplastic elastomer is preferably a polyether-ester block copolymer. The composition's glass
15 fibre content may vary within a wide range, for example between 20 and 70 wt.%, relative to the overall composition. Preferably the glass fibre content is between 30 and 60 wt.%. Most preferable is a glass fibre content of between 35 and 55 wt.%.

20 The glass fibre content to be chosen will depend primarily on the stiffness of the product to be realized. Preferably the stiffness is characterized by a flexural modulus of at least approx. 2000 MPa.

Elastomer compositions having such a high
25 glass fibre content are known, but are not marketed for injection-moulding applications.

The type of glass fibre may vary in kind of glass, sizing and dimensions. The type chosen will depend primarily on the mechanical properties to be
30 realized. To this end the fibre is usually provided with

- 4 -

a sizing that ensures a strong bond between the glass fibre and the thermoplastic elastomer matrix. A person skilled in the art will easily be able to make this choice from the glass fibres available on the market on the basis of specific experiments.

The aspect ratio (length/diameter) of the fibre in the composition is preferably chosen to be as high as possible, for example at least about 20; preferably the aspect ratio is at least 30, more preferably at least 40. These preferred aspect ratios do however not preclude the possibility of obtaining satisfying results for specific applications with glass fibres having a lower aspect ratio, too. The fibres' diameter is usually between 1.5 and 35 μm , fibres having a diameter of $< 15 \mu\text{m}$ being preferred.

In producing for example housings of electric and electronic equipment it is in many cases advantageous for the composition to contain also fibres of a material that absorbs electromagnetic radiation, for example steel fibres. These fibres are added in an amount such that sufficient protection is obtained. This is determined separately in each individual case.

The composition may also contain the usual additives, for example stabilizers against thermal oxidative influences and against the influence of light, processing auxiliaries, for example flow-promoting agents, in particular polytetrafluoroethylene, colourants and pigments, fillers, for example clay and/or talc and optionally flame retardants.

The thermoplastic elastomer used as the

matrix material is chosen from the group comprising polyurethanes, styrene block copolymers and polyester block copolymers. These polymers are described for example in Chapters 2, 3 and 4 and 8 and 9, respectively, of the book 'Thermoplastic Elastomers', 2nd Ed., Hanser Verlag, Munich (1996) ISBN 1-56990-205-4, to which reference is made for detailed information.

For practical reasons, in particular the highly critical processing conditions, for example the requirement of a low moisture content and the long time that is required after the processing for the product to obtain approximately its ultimate mechanical properties, thermoplastic polyurethane elastomers are however not preferable.

While they are being processed, styrene block copolymers present the problem that the melt viscosity is highly dependent on the shear force and is very high especially at low shear forces, as a result of which processing via injection moulding, though possible, imposes very high demands.

Therefore polyester block copolymers are preferred, more in particular the polyether-ester block copolymers. They may optionally be mixed with a crystalline polyalkylene ester, for example polybutylene terephthalate (PBT). It has most surprisingly been found that a product that is pleasant to touch and has a perfect surface is obtained with these thermoplastic elastomer compositions in one single-step injection-moulding operation. The stiffness of the product obtained in injection-moulding can be varied by

- 6 -

modifying the elastomer matrix and the glass fibre content.

The choice of the polyether-ester block copolymer presents the additional advantage that a relatively large degree of variation in stiffness can be realized without the surface properties varying substantially. On account of the crystallisation rate, polyether-ester block copolymers comprising hard segments composed of butylene terephthalate or butylene naphthalate units are preferred. As the units for the soft segments, use is preferably made of alkylene oxide units having 2 to 8 C atoms; preferably the soft segments are composed of predominantly propylene oxide and/or butylene oxide units. Block copolymers based on ethylene oxide present the drawback that they can absorb large amounts of water and the product obtained therefrom hence shows inferior dimensional stability. For the same reason the polyether-ester block copolymers are preferable to the polyester-ester and the polyether-amide block copolymers.

Preferably the molecular weight of the soft segments is chosen to be between 400 and 3000 and the soft segment concentration between 10 and 65 wt.%, preferably between 20 and 60 wt.% of the polyether-ester block copolymer. The Shore D hardness of the matrix may then vary between 30 and 75, preferably between 30 and 50 (measured according to ISO R 868). A very great advantage in this context is the unusual phenomenon that, in spite of a high glass fibre content, the hardness of the reinforced softer polyether esters is

only slightly higher than that of the non-reinforced, and the high stiffness required can be realized without appreciable concessions with respect to the pleasant tactile properties.

5 The mol. weight of the thermoplastic elastomer is preferably chosen so that the melt viscosity, expressed as melt flow index, MFI, measured at 230°C and 2.16 kg according to ASTM D1238, in g/10 min., is between 50 and 10, preferably between 30 and 10 15; most preferable is an MFI of about 25 g/10 minutes.

The injection moulding is carried out under the conditions usually applied for the thermoplastic elastomer concerned. These conditions are specified in the product brochures by the raw material supplier.

15 The glassfibres-containing thermoplastic elastomer composition can be obtained from the composite components in the usual manners, for example by mixing the polymer in the solid phase in the form of a powder or granulate with the glass fibres. This composition can 20 then be fed directly to the injection-moulding machine's extruder. In another process, which is generally preferred, glass fibres and thermoplastic elastomer and optionally other additives are mixed in the melt. The usual melt-mixing equipment can be used for this 25 purpose. Preferably an extruder is used. Glass fibres and thermoplastic elastomer can then be fed to the throat simultaneously; in another embodiment the elastomer is first melted, after which the glass fibres are fed to the melt. In the latter case a greater fibre 30 length can be realized in the composition, which has a

positive effect on the stiffness of the injection-moulded product. Good dispersion of the glass fibres in the product according to the invention is obtained especially when the glass fibres have been mixed into
5 the melt before the injection-moulding already.

The term 'pleasant to touch' is a subjective measure, which can still not be characterized in a single physical parameter, in spite of extensive research. Parameters such as roughness, hardness and the
10 surface's resistance to friction play a part in this respect. Producers of consumer articles therefore use so-called touch panels to obtain the most accurate possible average evaluation of a surface. Such a qualitative evaluation will be used in the examples in
15 this application.

Experimental

Unless otherwise indicated, the compositions were obtained by mixing with the aid of a Werner and
20 Pfleiderer ZSK 53 twin-screw extruder. The glass fibre was fed to the already melted polymer. The compositions obtained were injection-moulded to form specimens for mechanical tests, and mobile telephone housings for tests by a panel of users. Mobile telephone housings
25 obtained according to the state of the art, i.e. by means of sequential moulding of ABS/PC and a coating of polyurethane and by means of injection moulding of ABS/PC with a textured surface, were also tested by the panel.

Materials employed

Hytrel[®] polyether-ester block copolymer¹⁾, Shore D
hardness 52, from DuPont de Nemours

Arnitel[®]E, polyether-ester block copolymer¹⁾, Shore D
5 hardness 40-55, from DSM

Arnitel[®]P, polyether-ester block copolymer²⁾, Shore D
hardness 38, from DSM

Elastollan[®] 1185A10 polyether-urethane block copolymer,
Shore D hardness 39, from Elastogram/BASF (MFIs 90 and
10 8, resp.)

Glass fibre: OCF[®]429YZ from Owens-Corning, l = 4.5 mm; d
= 10 µm.

The invention will now be further elucidated
with reference to the following examples and comparative
15 examples, without however being limited thereto.

Examples

Test methods.

The surface of the products obtained was
20 characterized with the aid of the following tests:

Hardness: Shore D according to ISO R 868

Perfection: by visual inspection

+ no appreciable observable irregularities

0 a few imperfections

25 - irregular surface

¹ based on polybutylene terephthalate hard segments and tetramethylene
oxid soft segments.

² based on polybutylene terephthalate hard segments and thylene-oxide-
terminated polypropylene oxide soft segments

- 10 -

Tactile properties: this subjective evaluation was objectified as much as possible by averaging the evaluations of a panel of users.

+ pleasant according to at least 80% of the panel

5 members

0 indifferent

- has negative aspects according to at least 80% of the panel members

Flexural properties: flexural modulus ISO 178

10 Impact resistance: Izod notched ISO R 180 (23°C)

MFI: ASTM D1238.

The tested compositions and results are presented in Table I.

15 Comparative experiments

Telephone housings obtained according to the state of the art, i.e.

A) ABS + PC coated with a polyurethane with long alcohol segments and

20 B) ABS + PC with a textured surface, were evaluated as (+) and indifferent (0), respectively, by the panel members.

It was commented that the telephone housing with a textured surface tended to slip from the hands.

25

Table I

Polymer	Glass fibre content [wt. %]	MPI (gr/10 min.)	Shore D hardness	Flexural modulus [Npa]	Impact resistance [KJ/m^2] q	Surface		Comments
						perfection	touch	
Hytral 5557M (D55)	20	43* (230°C)	64	1190	20	0	+	insufficiently stiff
	30		70	2240	18	0	0	
Amitel EL550 (D53)	34	25*	63	3000	23	+	+	
	19	26*, 18 (230°C)	44	780	30	+	+	insufficiently stiff
EM400 (D38)	34	16	45	1320	26	+	+	
	46, 6	13	48	2410	24	+	+	
	31, 4		52	1920	22	+	+	
EM460 (D45)	37, 4		54	2236	21	+	+	
	0	17* (240°C)	70	1045	12	+	+	insufficiently stiff

Polymer	Glass fibre content (wt. %)	MFI (gr/10 min.)	Shore D hardness	Flexural modulus (Mpa)	Impact resistance (KJ/m ²)q	Surface		Comments
						perfection	touch	
PL360 (D38)	30	20*, 15 (230)	46	1487	27	+	+	
	38	13	52	2121	25	0	+	
	50	10	58	2800	23	0	+	
Elastollan (D39)	30	90* (190)**	50			+	+	
	30	8* (190)	49			-	0	

* MFI non-reinforced polymer according to supplier's specifications

** The unmarked values measured in the composition.

CLAIMS

1. Process for producing a product having a soft touch, comprising the single-step injection
5 moulding of a thermoplastic elastomer composition, chosen from the group comprising polyester block copolymers, polyurethanes and styrene block copolymers, which contains glass fibre.
2. Process according to Claim 1, characterized in that
10 the thermoplastic elastomer is a polyether-ester block copolymer.
3. Process according to Claim 1 or Claim 2, characterized in that the glass fibre content is 20-70 wt.%, relative to the overall composition.
- 15 4. Process according to Claim 3, characterized in that the glass fibre content is 35-55 wt.%, relative to the overall composition.
5. Process according to any one of the above claims, characterized in that the hardness of the
20 thermoplastic elastomer expressed as Shore D lies between 30 and 75, preferably between 30 and 50.
6. Process according to any one of the above claims, characterized in that the melt viscosity of the thermoplastic elastomer, expressed as melt flow
25 index, MFI, measured at 230°C and 2.16 kg according to ASTM D1238, in g/10 minutes, is between 50 and 10, preferably between 30 and 15.
7. Product obtained by the process according to any one of the above claims, characterized in that its
30 stiffness expressed as the flexural modulus is at

least 2000 MPa.

8. Product obtained by the process according to any one of Claims 1-6, characterized in that its Shore D hardness is less than 60.

INTERNATIONAL SEARCH REPORT

Inter: al Application No

PCT/NL 98/00522

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08L53/00 C08L75/04 C08L87/00 C08K7/14

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08K C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DATABASE WPI Section Ch, Week 7522 Derwent Publications Ltd., London, GB; Class A23, AN 75-36698W XP002064705 & JP 50 008850 A (TOYO SPINNING CO LTD) , 29 January 1975 see abstract	1-5
X	PATENT ABSTRACTS OF JAPAN vol. 13, no. 299 (M-847), 11 July 1989 & JP 01 090714 A (INOUE MTP CO LTD), 7 April 1989 see abstract	1,3,4
X	DE 23 50 852 A (BASF AG) 17 April 1975 see page 6; examples 1-5 --- -/--	1,3,4



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"Z" document member of the same patent family

Date of the actual completion of the international search

9 December 1998

Date of mailing of the international search report

23/12/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Siemens, T

INTERNATIONAL SEARCH REPORT

Intern 1st Application No
PCT/NL 98/00522

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 37 39 122 A (PEBRA GMBH) 1 June 1989 see column 1, line 63 - line 67 ---	1
X	DE 39 38 891 A (PHOENIX AG) 31 May 1990 see claims 1,6 ---	1,3
X	DE 40 15 714 A (BAYER AG) 21 November 1991 see claims 1-3 -----	1,3,4

1

Form PCT/ISA/210 (continuation of second sheet) (July 1992)

page 2 of 2

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/NL 98/00522

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE 2350852 A	17-04-1975	BE 820807 A FR 2247506 A GB 1475562 A JP 50078649 A NL 7413354 A	08-04-1975 09-05-1975 01-06-1977 26-06-1975 14-04-1975
DE 3739122 A	01-06-1989	DE 3886768 D WO 8904751 A EP 0389507 A JP 3500991 T JP 4042171 B US 5372491 A	10-02-1994 01-06-1989 03-10-1990 07-03-1991 10-07-1992 13-12-1994
DE 3938891 A	31-05-1990	NONE	
DE 4015714 A	21-11-1991	NONE	